

# COSMOPLENE® AZ564

Polypropylene Copolymer

TPC, The Polyolefin Company (Singapore) Pte Ltd

## Message:

COSMOPLENE AZ564 is high impact PP copolymer manufactured by gas phase process licensed from Sumitomo Chemical Co. Japan.

COSMOPLENE AZ564 is high flow, high stiffness, high impact copolymer grade which can perform faster injection cycle and thinner gauge.

COSMOPLENE AZ564 is specially designed for large item, wide area, thin gauge, low stress products such as tub and lid of washing machine, thin wall containers, TV back cover, automotive door trims etc.

General Information			
Features	High Flow		
	High Impact Resistance		
	High Stiffness		
	Impact Copolymer		
Uses	Appliance Components		
	Automotive Applications		
	Thin-walled Containers		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.1a		
UL File Number	E108370		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	30	g/10 min	ASTM D1238
Molding Shrinkage			Internal Method
Flow : 2.00 mm	1.5	%	
Across Flow : 2.00 mm	1.5	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	26.5	MPa	
Break	19.0	MPa	
Tensile Elongation (Break)	150	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	40	J/m	
23°C	71	J/m	

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	121	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	190 to 230	°C	
Middle Temperature	190 to 230	°C	
Front Temperature	190 to 230	°C	
Mold Temperature	30.0	°C	
Injection Pressure	6.86	MPa	
Clamp Tonnage	0.98	kN/cm <sup>2</sup>	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

