## Bamtac BTR620A

Styrene Butadiene Styrene Block Copolymer Ningbo Bamtac New Material Col, Ltd.

## Message:

BTR620A, which includes the compounds of SBS resin with bamboo fiber, maintains the antibiosis and deodorization features of bamboo. This products have been successfully applied in handle coating and it also can be applied in shoes material and toys, like bassinet wheel, cushion and ects....

General Information			
Filler / Reinforcement	Bamboo Fiber		
Uses	Footwear		
	Toys		
Physical	Nominal Value	Unit	Test Method
Density	0.980 to 1.07	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	20 to 25	g/10 min	ISO 1133
Shrinkage	0.50 to 1.0	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	65 to 70		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	> 20.0	MPa	ISO 527-2
Tensile Stress	> 2.00	MPa	ISO 527-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

ISO 527-2

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

> 500

Tel: +86 21 5895 8519

Tensile Strain (Break)

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

