

Ultramid® B3ZG3

Polyamide 6

BASF Corporation

Message:

Ultramid B3ZG3 is an impact-modified, 15% glass fiber reinforced injection molding PA6 grade.

Applications

Typical applications include automobile cable conduits.

General Information				
UL YellowCard		E36632-531664	E41871-233706	
Filler / Reinforcement		Glass Fiber,15% Filler by Weight		
Additive		Impact Modifier		
Features		Impact Modified		
		Oil Resistant		
Uses		Automotive Applications		
		Conduit		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS Compliant		
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.22	--	g/cm ³	ASTM D792, ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	35.0	--	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.18 mm)	0.50	--	%	
Water Absorption				
Saturation	7.5	--	%	ASTM D570
Saturation, 23°C	7.5	--	%	ISO 62
Equilibrium, 50% RH	2.4	--	%	ASTM D570
Equilibrium, 23°C, 50% RH	2.4	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	5500	2900	MPa	ISO 527-2
Tensile Strength				
Break, 23°C	103	--	MPa	ASTM D638
Break, 23°C	110	60.0	MPa	ISO 527-2
Tensile Elongation				
Break, 23°C	4.0	--	%	ASTM D638
Break, 23°C	4.0	18	%	ISO 527-2

Flexural Modulus				
23°C	4480	--	MPa	ASTM D790
23°C	4500	2500	MPa	ISO 178
Flexural Stress (23°C)	150	80.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-30°C	7.0	--	kJ/m ²	
23°C	16	30	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179
-30°C	55	--	kJ/m ²	
23°C	75	110	kJ/m ²	
Notched Izod Impact				
-40°C	53	--	J/m	ASTM D256
23°C	110	--	J/m	ASTM D256
23°C	15	29	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	204	--	°C	ASTM D648
0.45 MPa, Unannealed	200	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	193	--	°C	ASTM D648
1.8 MPa, Unannealed	180	--	°C	ISO 75-2/A
Peak Melting Temperature	220	--	°C	ASTM D3418, ISO 3146
CLTE				
Flow	3.3E-5	--	cm/cm/°C	
Transverse	7.5E-5	--	cm/cm/°C	
RTI Elec				UL 746
0.730 mm	150	--	°C	
1.50 mm	150	--	°C	
3.00 mm	150	--	°C	
RTI Imp				UL 746
0.730 mm	115	--	°C	
1.50 mm	115	--	°C	
3.00 mm	120	--	°C	
RTI Str				UL 746
0.730 mm	150	--	°C	
1.50 mm	150	--	°C	
3.00 mm	150	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity				
1.50 mm	1.0E+13	1.0E+10	ohms · cm	ASTM D257

--	1.0E+13	1.0E+10	ohms·cm	IEC 60093
Dielectric Constant (1 MHz)	3.70	6.20		IEC 60250
Dissipation Factor (1 MHz)	0.025	0.20		IEC 60250
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.730 mm	HB	--		
1.50 mm	HB	--		
3.00 mm	HB	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	2.0 to 4.0		hr	
Suggested Max Moisture	0.080		%	
Rear Temperature	245 to 275		°C	
Middle Temperature	260 to 285		°C	
Front Temperature	270 to 295		°C	
Nozzle Temperature	270 to 295		°C	
Processing (Melt) Temp	270 to 295		°C	
Mold Temperature	80.0 to 95.0		°C	
Injection Pressure	3.50 to 12.5		MPa	
Injection Rate	Fast			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

