

OP - PC - Filled 30GF

Polycarbonate

Oxford Polymers

Message:

OP - PC - Filled 30GF is a Polycarbonate (PC) material filled with 30% glass fiber. It is available in North America for injection molding.

General Information			
UL YellowCard	E186411-100652252		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8620	MPa	ASTM D638
Tensile Strength (Break)	131	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	159	MPa	ASTM D790
Compressive Strength	124	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	152	°C	
1.8 MPa, Unannealed	146	°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	288 to 293	°C	
Middle Temperature	299 to 316	°C	
Front Temperature	299 to 316	°C	
Nozzle Temperature	299 to 316	°C	
Processing (Melt) Temp	293	°C	
Mold Temperature	82.2 to 116	°C	
Injection Pressure	103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT