

LNP™ LUBRICOMP™ WFL34H compound

Polybutylene Terephthalate

SABIC Innovative Plastics

Message:

LNP LUBRICOMP WFL34H is a compound based on Polybutylene Terephthalate resin containing PTFE, Glass Fiber. Added features of this material include: Internally Lubricated.

Also known as: LNP* LUBRICOMP* Compound WFL-4034 HC

Product reorder name: WFL34H

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Additive	PTFE lubricant		
Features	Lubrication		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.56	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	7940	MPa	ASTM D638
Tensile Strength (Break)	115	MPa	ASTM D638
Tensile Elongation (Break)	2.8	%	ASTM D638
Flexural Modulus	7430	MPa	ASTM D790
Flexural Strength	165	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	85	J/m	ASTM D256
Unnotched Izod Impact (23°C)	740	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	214	°C	ASTM D648
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT