

EPO-TEK® EK1000-MP

Epoxy; Epoxide

Epoxy Technology Inc.

Message:

A single component, silver-filled adhesive that exhibits exceptional thermal and electrical conductivity along with a shiny silver appearance making it ideal for the demanding requirements of high power LED die attach applications. Designed specifically to meet the requirements pertaining to the MIL-STD883/Test Method 5011 for military hybrids. Other benefits include low viscosity and high thixotropy making it suitable for a wide range of application techniques.

General Information		
Filler / Reinforcement	Silver	
Features	Electrically Conductive	
	Low Viscosity	
	Thermally Conductive	
	Thixotropic	
Uses	Adhesives	
	Electrical/Electronic Applications	
	LEDs	
Agency Ratings	EC 1907/2006 (REACH)	
	EU 2003/11/EC	
	EU 2006/122/EC	
	MIL Std. 883	
RoHS Compliance	RoHS Compliant	
Forms	Paste	
Physical	Nominal Value	Unit
Ion Type		
Cl-	< 200	ppm
K+	< 50	ppm
Na+	< 50	ppm
NH4+	5	ppm
Particle Size	< 45.0	µm
Dry Time	< 1.0	day
Degradation Temperature	357	°C
Die Shear Strength		
> 10 kg : 23°C ¹	23.4	MPa
> 5 kg : 23°C ²	11.7	MPa
Operating Temperature		
Continuous	-55 to 200	°C

Intermittent	-55 to 300	°C
Storage Modulus	1.89	GPa
Thixotropic Index	3.60	
Weight Loss on Heating		
200°C	0.19	%
250°C	0.94	%
300°C	1.7	%
Thermal	Nominal Value	Unit
Glass Transition Temperature ³	> 80.0	°C
CLTE - Flow		
-- ⁴	3.8E-5	cm/cm/°C
-- ⁵	9.4E-5	cm/cm/°C
Thermal Conductivity		
-- ⁶	13	W/m/K
-- ⁷	26	W/m/K
Thermoset	Nominal Value	Unit
Shelf Life (-40°C)	52	wk
Uncured Properties	Nominal Value	Unit
Color	Silver	
Density	3.33	g/cm ³
Viscosity ⁸ (23°C)	1.8 to 3.6	Pa·s
Curing Time (200°C)	1.0	hr
Pot Life	20000	min
Cured Properties	Nominal Value	Unit
Shore Hardness (Shore D)	66	
Lap Shear Strength (23°C)	6.96	MPa
Volume Resistivity	< 9.0E-5	ohms·cm
NOTE		
1.	Initial	
2.	After 1000 hrs 85°C/85%RH	
3.	Dynamic Cure 20-200°C/ISO 25 Min; Ramp -10-200°C @ 20°C/Min	
4.	Below Tg	
5.	Above Tg	
6.	150°C/1 Hour Cure	
7.	150°C/1 Hour+200°C/1 Hour Cure	
8.	100 rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

