

Vydyne® R550H NT453

Polyamide 66

Ascend Performance Materials Operations LLC

Message:

Vydyne R550H NT453 is general-purpose, heat-stabilized, hydrolysis-resistant, 50% glass-fiber reinforced PA66 resin. Available in natural, it is specifically designed to maximize the retention of physical properties when exposed to anti-freeze solutions at elevated temperatures. This product is also lubricated for improved flow and offers superior surface appearance.

Glass-reinforced Vydyne resins provide higher heat distortion temperature, resistance to creep and better dimensional stability when compared with unreinforced PA66. These products have good chemical resistance to a broad range of chemicals including gasoline, hydraulic fluids and most solvents. Vydyne R550H NT453 is heat-stabilized to minimize oxidative degradation of the polymer when exposed to elevated temperatures in service. This product provides improved retention of physical properties under exposure to long term heat. Also, Vydyne R550H NT453 has excellent knit-line strength and fatigue resistance, which is essential for cycle testing with anti-freeze solutions.

Typical Applications/End Uses:

Vydyne R550H NT453 is successfully used in a wide range of injection-molding engineering applications. Typical parts include automotive clips, radiator endtanks and parts of the air-conditioning and fuel distribution systems; electrical connectors, housings and bobbins; and industrial applications such as gears, bearing shells, covers and housings.

General Information				
Filler / Reinforcement		Glass Fiber,50% Filler by Weight		
Additive		Heat Stabilizer		
		Lubricant		
Features		Good Flow		
		Good Mold Release		
		Heat Stabilized		
		High Rigidity		
		High Strength		
		Lubricated		
Uses		Automotive Under the Hood		
		Gears		
		Housings		
		Power/Other Tools		
Agency Ratings		ASTM D 4066 PA012G50		
		ASTM D 6779 PA012G50		
UL File Number		E70062		
Appearance		Natural Color		
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.58	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4

Across Flow : 23°C, 2.00 mm	0.90	--	%	
Flow : 23°C, 2.00 mm	0.40	--	%	
Water Absorption				ISO 62
23°C, 24 hr	0.50	--	%	
Equilibrium, 23°C, 50% RH	1.2	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	16800	15200	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	240	190	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.5	2.8	%	ISO 527-2
Flexural Modulus (23°C)	16000	11200	MPa	ISO 178
Flexural Strength (23°C)	350	270	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	14	15	kJ/m ²	
23°C	15	21	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	91	95	kJ/m ²	
23°C	95	110	kJ/m ²	
Notched Izod Impact Strength				ISO 180
-30°C	16	18	kJ/m ²	
23°C	17	21	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	260	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	255	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	1.2E-5	--	cm/cm/°C	
Transverse : 23 to 55°C, 2.00 mm	1.0E-4	--	cm/cm/°C	
RTI Elec				UL 746
0.750 mm	140	--	°C	
1.50 mm	140	--	°C	
3.00 mm	140	--	°C	
RTI Imp				UL 746
0.750 mm	130	--	°C	
1.50 mm	130	--	°C	

3.00 mm	130	--	°C	
RTI Str				UL 746
0.750 mm	140	--	°C	
1.50 mm	140	--	°C	
3.00 mm	140	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.750 mm)	1.0E+12	--	ohms·cm	IEC 60093
Dielectric Strength (1.00 mm)	20	--	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	PLC 5	--		ASTM D495
Comparative Tracking Index (3.00 mm)	400 to 599	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.750 mm	PLC 0	--		
1.50 mm	PLC 0	--		
3.00 mm	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 1	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.750 mm	PLC 4	--		
1.50 mm	PLC 3	--		
3.00 mm	PLC 4	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.750 mm	HB	--		
1.50 mm	HB	--		
3.00 mm	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.750 mm	675	--	°C	
1.50 mm	675	--	°C	
3.00 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.750 mm	700	--	°C	
1.50 mm	700	--	°C	
3.00 mm	750	--	°C	
Additional Information	Dry	Conditioned		Test Method
Automotive Materials - (thickness d = 1mm)	+	--		FMVSS 302
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0		hr	

Suggested Max Regrind	25	%
Rear Temperature	280 to 310	°C
Middle Temperature	280 to 310	°C
Front Temperature	280 to 310	°C
Nozzle Temperature	280 to 310	°C
Processing (Melt) Temp	285 to 305	°C
Mold Temperature	65.0 to 95.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT