

KOPA® KN126

Polyamide 6
Kolon Plastics, Inc.

Message:

KOPA® KN126 is a Polyamide 6 (Nylon 6) product. It is available in Asia Pacific, Europe, Latin America, or North America. Applications of KOPA® KN126 include automotive and engineering/industrial parts.

Characteristics include:

- Flame Rated
- Lubricated
- Medium Viscosity

General Information			
Additive	Lubricant		
Features	Medium Viscosity		
Uses	Automotive Applications		
	Industrial Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.3 to 1.5	%	ASTM D955
Water Absorption (Equilibrium)	1.8	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	82.0	MPa	ASTM D638
Tensile Elongation (Yield)	90	%	ASTM D638
Flexural Modulus	2940	MPa	ASTM D790
Flexural Strength	128	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	180	°C	
1.8 MPa, Unannealed	65.0	°C	
Melting Temperature	220	°C	
CLTE - Flow	8.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.40		ASTM D150
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

