Karina IVORY PVC COMPOUND 760-35/1-IS-SD

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

PVC COMPOUND FOR EXTRUSION OF MONOFILAMENT.

General Information			
Uses	Monofilaments		
Appearance	lvory		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.23 to 1.29	g/cm³	ASTM D792
Color a	-5.74 to 0.260		ME 12
Color b	3.20 to 4.80		ME 12
Color L	80.4 to 86.4		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	74 to 78		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 39.2	MPa	ASTM D638
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

