

Elastron® G G401.A25.B

Styrene Ethylene Butylene Styrene Block Copolymer

Elastron USA, Inc.

Message:

A soft, black unfilled SEBS based thermoplastic elastomer (TPE) compound which has very good physical properties and chemical resistance. This product is a good option when good scratch and abrasion resistance is required.
Bondable to: PP, EVA, PE

| General Information | | | |
|------------------------------|--------------------------|-------------------|-------------|
| Features | Block Copolymer | | |
| | Bondability | | |
| | Good Abrasion Resistance | | |
| | Good Chemical Resistance | | |
| | Scratch Resistant | | |
| | Soft | | |
| RoHS Compliance | RoHS Compliant | | |
| Appearance | Black | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.880 | g/cm ³ | ASTM D792 |
| Molding Shrinkage | | | ASTM D955 |
| Flow | 3.9 | % | |
| Across Flow | 1.4 | % | |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 25 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress | | | ASTM D412 |
| 100% Strain | 0.600 | MPa | |
| 300% Strain | 1.10 | MPa | |
| Tensile Strength (Break) | 3.50 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 1000 | % | ASTM D412 |
| Tear Strength | 32.0 | kN/m | ASTM D624 |
| Compression Set | | | ASTM D395 |
| 23°C, 22 hr | 8.0 | % | |
| 70°C, 22 hr | 41 | % | |
| 100°C, 22 hr | 65 | % | |
| Additional Information | Nominal Value | | Test Method |

| Ozone Resistance - Stressed | No Cracks | ASTM D518 |
|-----------------------------|---------------|-----------|
| Injection | Nominal Value | Unit |
| Suggested Max Regrind | 20 | % |
| Rear Temperature | 145 to 175 | °C |
| Middle Temperature | 155 to 185 | °C |
| Front Temperature | 160 to 190 | °C |
| Nozzle Temperature | 175 to 205 | °C |
| Mold Temperature | 25.0 to 50.0 | °C |
| Extrusion | Nominal Value | Unit |
| Cylinder Zone 1 Temp. | 150 to 170 | °C |
| Cylinder Zone 2 Temp. | 155 to 175 | °C |
| Cylinder Zone 3 Temp. | 165 to 185 | °C |
| Cylinder Zone 4 Temp. | 175 to 205 | °C |
| Cylinder Zone 5 Temp. | 180 to 210 | °C |
| Die Temperature | 190 to 210 | °C |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

