

Resinoid 2020

Phenolic

Resinoid Engineering Corporation

Message:

Resinoid 2020 is a Phenolic product. It can be processed by compression molding, injection molding, or resin transfer molding and is available in North America. Applications of Resinoid 2020 include automotive and electrical/electronic applications.

General Information	
UL YellowCard	E61847-247060
Uses	Automotive Applications Electrical Parts
Appearance	Black
Forms	Pellets
Processing Method	Compression Molding Injection Molding Resin Transfer Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Bulk Factor	10		ASTM D1895
Molding Shrinkage - Flow	0.25 to 0.35	%	ASTM D955
Water Absorption (24 hr)	0.50	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	48.3	MPa	ASTM D638
Compressive Strength	159	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	204	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	8.7	kV/mm	ASTM D149
Arc Resistance	115	sec	ASTM D495

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

