

RX® 1310

Diallyl Phthalate

Sumitomo Bakelite North America, Inc.

Message:

RX® 1310 is a short glass fiber reinforced, non-flame retardant, diallyl ortho-phthalate molding compound, which meets the requirements of ASTM D5948 Type SDG.

General Information	
Filler / Reinforcement	Glass Fiber
Agency Ratings	ASTM D 5948, Type SDG
Appearance	Black
	Brown
	Green
Forms	Granules
Processing Method	Compression Molding
	Resin Transfer Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.83	g/cm ³	ASTM D792
Apparent Density	0.75	g/cm ³	ASTM D1895
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D955
Water Absorption - 48 hr (50°C)	0.25	%	ASTM D570

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	76.0	MPa	ASTM D638
Flexural Modulus	12400	MPa	ASTM D790
Flexural Strength	124	MPa	ASTM D790
Compressive Strength	150	MPa	ASTM D695

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	37	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	205	°C	ASTM D648
CLTE - Flow	2.1E-5	cm/cm/°C	ASTM E831
Thermal Conductivity	0.28	W/m/K	ASTM C518
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	130	°C	UL 746

Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	12	kV/mm	ASTM D149
Dielectric Constant ¹			ASTM D150

1 kHz	4.00		
1 MHz	3.50		
Dissipation Factor ²			ASTM D150
1 kHz	9.0E-3		
1 MHz	0.016		
Arc Resistance	130	sec	ASTM D495
Comparative Tracking Index	> 600	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	26	%	ASTM D2863
NOTE			
1.	Wet		
2.	Wet		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT