Plaslube® PA6 TL10

Polyamide 6

Techmer Engineered Solutions

Message:

Plaslube® PA6 TL10 is a Polyamide 6 (Nylon 6) product. It can be processed by injection molding and is available in North America. Characteristics include:

Heat Stabilizer

Lubricated

General Information					
Additive	Heat Stabilizer				
	PTFE Lubricant (10%)				
Features	Heat Stabilized				
	Lubricated				
Appearance	Colors Available				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.20	g/cm³	ASTM D792		
Molding Shrinkage - Flow (3.18 mm)	1.7	%	ASTM D955		
Water Absorption (24 hr)	1.0	%	ASTM D570		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	116		ASTM D785		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	64.8	MPa	ASTM D638		
Tensile Elongation (Break)	9.5	%	ASTM D638		
Flexural Modulus	2690	MPa	ASTM D790		
Flexural Strength	82.7	MPa	ASTM D790		
Coefficient of Friction			ASTM D1894		
vs. Steel - Dynamic	0.20				
vs. Steel - Static	0.14				
Wear Factor	100	10^-8 mm³/N·m	ASTM D3702		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C, 3.18 mm)	48	J/m	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		
Deflection Temperature Under Load			ASTM D648		
0.45 MPa, Unannealed	160	°C			
1.8 MPa, Unannealed	76.7	°C			
CLTE - Flow	8.5E-5	cm/cm/°C	ASTM D696		

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength ¹	20	kV/mm	ASTM D149
NOTE			

. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

