

# UBESTA 3030XA

Polyamide 12

UBE America, Inc.

## Message:

UBESTA 3030XA is a polyamide 12 (nylon 12) material. This product is available in North America.

The typical application fields of UBESTA 3030XA are: movies

General Information			
Uses	Films		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	42.0	MPa	ASTM D638
Fracture, 23°C	54.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	250	%	ASTM D638
Flexural Modulus (23°C)	1420	MPa	ASTM D790
Flexural Strength (23°C)	55.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	145	°C	ASTM D648
Melting Temperature	178	°C	
Additional Information			

The value listed as Melting Point was tested in accordance with ASTM D3418.Tensile Strength at Break, ASTM D638, 23°C: >54 MPaTensile Elongation at Break, ASTM D638, 23°C: >250%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

