

Fluon® PTFE RA7003

Polytetrafluoroethylene

Asahi Glass Co., Ltd.

Message:

Fluon® PTFE FC has improved creep and wear resistance. A wide range of fillers such as glass fiber, graphite, bronze, carbon fiber are available. Properties of each grades are listed later in tables.

Features:

Semi-conductive

Anti-static

General Information		
Filler / Reinforcement	Filler,3.0% Filler by Weight	
Features	Antistatic	
	Semi Conductive	
Forms	Powder	
Physical	Nominal Value	Unit
Specific Gravity		
--	2.12	g/cm ³
--	0.470	g/cm ³
Mechanical	Nominal Value	Unit
Tensile Strength	27.7	MPa
Tensile Elongation (Break)	300	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT