

CYCOLAC™ MGABS02 resin

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

General purpose ABS. Excellent flow/impact.

General Information		
UL YellowCard	E121562-220700	E121562-220701
Features	General Purpose	
	Good Flow	
	Good Impact Resistance	
Uses	General Purpose	
Processing Method	Injection Molding	
Multi-Point Data	Flexural DMA (ASTM D4065)	
	Pressure-Volume-Temperature (PVT - Zoller Method)	
	Shear DMA (ASTM D4065)	
	Specific Heat vs. Temperature (ASTM D3417)	
	Tensile Fatigue	
	Tensile Stress vs. Strain (ASTM D638)	
	Thermal Conductivity vs. Temperature (ASTM E1530)	
	Viscosity vs. Shear Rate (ASTM D3835)	

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	5.6	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	18.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.80	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2140	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	40.7	MPa	
Break	31.7	MPa	
Tensile Elongation ³			ASTM D638
Yield	2.0	%	
Break	20	%	
Flexural Modulus ⁴ (50.0 mm Span)	2210	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 50.0 mm Span)	68.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact (23°C)	290	J/m	ASTM D256
Instrumented Dart Impact (23°C, Total Energy)	30.3	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.20 mm	96.7	°C	
1.8 MPa, Unannealed, 3.20 mm	82.2	°C	
Vicat Softening Temperature	98.9	°C	ASTM D1525 ⁶
CLTE			ASTM E831
Flow : -40 to 40°C	8.8E-5	cm/cm/°C	
Transverse : -40 to 40°C	8.8E-5	cm/cm/°C	
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI Str	60.0	°C	UL 746
Electrical	Nominal Value		Test Method
Arc Resistance ⁷	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 0		UL 746
High Amp Arc Ignition (HAI)	PLC 0		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.52 mm)	HB		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (240°C, 1000 sec ⁻¹)	225	Pa · s	ASTM D3835
Injection	Nominal Value	Unit	
Drying Temperature	82.2 to 93.3	°C	
Drying Time	2.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.10	%	
Suggested Shot Size	50 to 70	%	
Rear Temperature	188 to 210	°C	
Middle Temperature	204 to 227	°C	
Front Temperature	216 to 238	°C	
Nozzle Temperature	218 to 260	°C	
Processing (Melt) Temp	218 to 260	°C	
Mold Temperature	48.9 to 71.1	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	30 to 60	rpm	
Vent Depth	0.038 to 0.051	mm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		

3.	Type I, 5.0 mm/min
4.	1.3 mm/min
5.	1.3 mm/min
6.	Rate B (120°C/h), Loading 2 (50 N)
7.	Tungsten Electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

