

Plexiglas® Satinice df22 zk6BR

Polymethyl Methacrylate Acrylic
Evonik Industries AG

Message:

PLEXIGLAS® Satinice df22 zk6BR, based on PLEXIGLAS® Resist zk6BR, is an impact modified molding compound characterized by diffuse scattering of light.

Typical properties of impact modified PLEXIGLAS® molding compound are

- high break resistance and impact strength
- improved resistance to stress cracking
- good weather resistance
- high surface hardness and mar resistance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® Satinice df22 zk6BR is characterized by the following special properties:

- very good lightdiffusion combined with excellent light transmission
- matte surfaces can be obtained by varying the extrusion parameters.

Application:

Used for extruding profiles and sheets, but also for injection molding items for lighting engineering applications

Examples:

applications that call for light diffusion combined with optimum transmission

General Information			
Additive	Impact Modifier		
Features	Good Weather Resistance		
	High ESCR (Stress Crack Resist.)		
	High Hardness		
	High Impact Resistance		
	High Strength		
	Light Stabilized		
Uses	Lighting Diffusers		
	Profiles		
	Sheet		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.15	g/cm³	ISO 1183

Melt Volume-Flow Rate (MVR) (230°C/3.8 kg)	1.40	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1800	MPa	ISO 527-2/1
Tensile Stress (Yield)	45.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	5.0	%	ISO 527-2/50
Nominal Tensile Strain at Break	40	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.5	kJ/m ²	ISO 179/1
Charpy Unnotched Impact Strength (23°C)	54	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	99.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	93.0	°C	ISO 75-2/A
Glass Transition Temperature	109	°C	ISO 11357-2
Vicat Softening Temperature	98.0	°C	ISO 306/B50
CLTE - Flow (0 to 50°C)	9.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Glow Wire Ignition Temperature	700	°C	IEC 60695-2-13
Fire Rating	B2		DIN 4102
Half-Value Angle	12.5	°	DIN 5036
Optical	Nominal Value	Unit	Test Method
Transmittance ¹	86.0	%	ISO 13468-2
Extrusion	Nominal Value	Unit	
Drying Temperature	< 85.0	°C	
Drying Time	2.0 to 3.0	hr	
Melt Temperature	230 to 260	°C	
Die Temperature	260	°C	
NOTE			
1.	D65		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT