Kingfa FRHIPS-100

High Impact Polystyrene

Kingfa

Message:

Kingfa FRHIPS-100 is a High Impact Polystyrene material. It is available in Asia Pacific or North America. Important attributes of Kingfa FRHIPS-100 are: Flame Rated Antistatic Flame Retardant Impact Resistant Rigid Typical applications include: Housings Appliances Household Applications

| General Information | | | |
|--|------------------------|----------|-------------|
| UL YellowCard | E171666-225767 | | |
| Additive | Antistatic | | |
| Features | Antistatic | | |
| | Flame Retardant | | |
| | High Impact Resistance | | |
| | High Rigidity | | |
| Uses | Appliances | | |
| | Electrical Housing | | |
| | Household Goods | | |
| | Housings | | |
| | 5 | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.18 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (200°C/5.0 kg) | 5.0 | g/10 min | ASTM D1238 |
| Molding Shrinkage - Flow (23°C) | 0.40 to 0.60 | % | ASTM D955 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness (R-Scale) | 90 | | ASTM D785 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ (23°C, Injection Molded) | 23.0 | MPa | ASTM D638 |
| Tensile Elongation ² (Break, 23°C, Injection Molded) | 40 | % | ASTM D638 |
| Flexural Modulus ³ (23°C, Injection Molded) | 2500 | MPa | ASTM D790 |
| Flexural Strength ⁴ (23°C, Injection Molded) | 36.0 | МРа | ASTM D790 |

| Impact | Nominal Value | Unit | Test Method |
|--|------------------------------------|---------|-------------------------|
| Notched Izod Impact (23°C, 3.20 mm, | | | |
| Injection Molded) | 95 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 | | | |
| MPa, Unannealed, 6.40 mm) | 75.0 | °C | ASTM D648 |
| Vicat Softening Temperature | 90.0 | °C | ASTM D1525 ⁵ |
| Electrical | Nominal Value | Unit | Test Method |
| Surface Resistivity | 1.0E+10 | ohms | ASTM D257 |
| Volume Resistivity | 1.0E+16 | ohms·cm | ASTM D257 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating (1.60 mm) | V-0 | | UL 94 |
| NOTE | | | |
| 1. | 50 mm/min | | |
| 2. | 50 mm/min | | |
| 3. | 2.0 mm/min | | |
| 4. | 2.0 mm/min | | |
| 5. | Rate B (120°C/h), Loading 1 (10 N) | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

