

Hostacom TRC 454N G81493

Polypropylene Copolymer
LyondellBasell Industries

Message:

Hostacom TRC 454N is an 8% talc filled PP copolymer, with high melt flow rate, excellent low temperature impact resistance and very good processability. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

For regulatory compliance information, see Hostacom TRC 454N G81493 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS). This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Features	Copolymer		
	Workability, good		
	High liquidity		
	Low temperature impact resistance		
Uses	Application in Automobile Field		
	Car interior equipment		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.950	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	19.0	MPa	ISO 527-2
Flexural Modulus ¹ (23°C)	1350	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	6.5	kJ/m ²	ISO 180/1A
23°C	45	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	52.0	°C	ISO 75-2/A
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

