

# Axiall PVC 19751

Flexible Polyvinyl Chloride

Axiall Corporation

## Message:

19751 is a compound formulated for a 105°C maximum service temperature rating recommended for general purpose insulation or jacket applications.

General Information			
Features	General		
Uses	Jacketing		
	Insulating material		
	General		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30 - 1.34	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	72 - 78		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5.86	MPa	ASTM D638
Tensile Strength	12.4	MPa	ASTM D638
Tensile Elongation (Break)	330	%	ASTM D638
Aging	Nominal Value	Unit	Test Method
Change in Ultimate Elongation in Air (136°C, 168 hr)	-15	%	UL 1581
Thermal	Nominal Value	Unit	
Melting Temperature	171	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	23	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT