

4LOY® 10E27300 FR1

Polycarbonate + ABS

4Plas

Message:

4LOY 10E27300 FR1 is a Standard Flow 85% PC / 15% ABS FR-V0 PC/ABS

General Information			
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2300	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	45.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	50	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	42	kJ/m ²	ISO 180/1A
23°C	46	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	125	°C	ISO 75-2/B
1.8 MPa, not annealed	90.0	°C	ISO 75-2/A
Vicat Softening Temperature	111	°C	ISO 306/B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	230 - 260	°C	
Mold Temperature	60.0 - 90.0	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	50.0 - 100	MPa	
Screw Speed	< 200	rpm	
Injection instructions			
Feed Throat Temperature: 60 - 80 °CBack Pressure: Low			
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

