# APEX® 90-A472R-55-NT

## Flexible Polyvinyl Chloride

## **Teknor Apex Company**

#### Message:

APEX® 90-A472R-55-NT is a Flexible Polyvinyl Chloride material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of APEX® 90-A472R-55-NT are:

Plasticized

Radiation (Gamma) Resistant

Sterilizable

Typical applications include:

Caps/Lids/Closures

Engineering/Industrial Parts

Medical/Healthcare

| General Information                  |                                 |       |             |
|--------------------------------------|---------------------------------|-------|-------------|
| Additive                             | Plasticizer                     |       |             |
| Features                             | DEHP Plasticizer                |       |             |
|                                      | Radiation (Gamma) Resistant     |       |             |
|                                      | Radiation Sterilizable          |       |             |
|                                      |                                 |       |             |
| Uses                                 | Caps                            |       |             |
|                                      | Medical/Healthcare Applications |       |             |
|                                      | Valves/Valve Parts              |       |             |
|                                      |                                 |       |             |
| Appearance                           | Clear/Transparent               |       |             |
| Forms                                | Pellets                         |       |             |
| Processing Method                    | Injection Molding               |       |             |
| Physical                             | Nominal Value                   | Unit  | Test Method |
| Specific Gravity                     | 1.15                            | g/cm³ | ASTM D792   |
| Hardness                             | Nominal Value                   | Unit  | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 55                              |       | ASTM D2240  |
| Mechanical                           | Nominal Value                   | Unit  | Test Method |
| Tensile Strength (Break)             | 9.65                            | MPa   | ASTM D638   |
| Tensile Elongation (Break)           | 370                             | %     | ASTM D638   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

