

LNP™ THERMOCOMP™ PF00ASXS

compound

Polyamide 6

SABIC Innovative Plastics

Message:

LNP THERMOCOMP* PF00ASXS is a compound based on Nylon 6 resin containing Glass Fiber. Added features of this material include: Heat Stabilized.

Also known as: LNP* THERMOCOMP* Compound PF-100-10 HS

Product reorder name: PF00ASXS

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Additive	heat stabilizer		
Features	Thermal Stability		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.57	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.10 - 0.30	%	ASTM D955
Transverse flow: 24 hours	0.60 - 0.70	%	ASTM D955
Vertical flow direction: 24 hours	0.60 - 0.80	%	ISO 294-4
Flow direction: 24 hours	0.10 - 0.30	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.83	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.97	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	17100	MPa	ASTM D638
--	17300	MPa	ISO 527-2/1
Tensile Strength			
Fracture	214	MPa	ASTM D638
Fracture	241	MPa	ISO 527-2
Tensile Elongation			
Fracture	2.8	%	ASTM D638
Fracture	3.0	%	ISO 527-2
Flexural Modulus			
--	12300	MPa	ASTM D790
--	12400	MPa	ISO 178
Flexural Strength			
--	329	MPa	ASTM D790

--	318	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	180	J/m	ASTM D256
23°C ²	19	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	95	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	18.3	J	ASTM D3763
--	22.5	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	198	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	210	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 - 0.25	%	
Rear Temperature	249 - 260	°C	
Middle Temperature	266 - 277	°C	
Front Temperature	277 - 288	°C	
Processing (Melt) Temp	266 - 277	°C	
Mold Temperature	82.2 - 93.3	°C	
Back Pressure	0.344 - 0.689	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT