

Flexirene® MS 26 A

Linear Low Density Polyethylene

Versalis S.p.A.

Message:

Flexirene MS 26 A is a linear low density polyethylene (LLDPE) with antioxidants, suitable for injection moulding application. Parts made by Flexirene MS 26 A are characterised by optimum low temperature properties. Flexirene MS 26 A is highly pure and it is suitable for all applications where good organoleptic properties are required.

Main Application

Flexirene MS 26 A is recommended for the production of lids, caps, closures and containers, and, is suggested for low temperature applications.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Food Contact Acceptable		
	Good Organoleptic Properties		
	High Purity		
	Low Density		
	Low Temperature Resistant		
Uses	Caps		
	Closures		
	Containers		
	Lids		
	Low Temperature Applications		
Agency Ratings	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.921	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	26	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, Injection Molded)	48		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield, Injection Molded	9.00	MPa	
Break, Injection Molded	10.0	MPa	
Tensile Strain (Break, Injection Molded)	> 500	%	ISO 527-2
Flexural Modulus (Injection Molded)	150	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method

Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	88.0	°C	ISO 306/A
Melting Temperature	115	°C	Internal Method
Injection	Nominal Value	Unit	
Rear Temperature	160 to 210	°C	
Middle Temperature	160 to 210	°C	
Front Temperature	160 to 210	°C	
Mold Temperature	10.0 to 40.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT