

Axiall PVC 8779

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

Non-lead stabilized, general purpose extrusion compound designed for PVC waterstops per Corps of Engineers Specification CRD-C 572-74.

General Information			
Features	General Purpose		
	Good Flexibility		
Uses	General Purpose		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	77		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant	6.21	MPa	ASTM D638
Tensile Strength	13.1	MPa	ASTM D638
Tensile Elongation (Yield)	370	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-38.0	°C	ASTM D746

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT