

ADEKA EP-4300E

Epoxy; Epoxide
Adeka Corporation

Message:
Low viscosity type of EP-4100
Electrics, cast molding

General Information		
Features	Low Viscosity	
Uses	Electrical/Electronic Applications	
Processing Method	Casting	
Physical	Nominal Value	Unit
Specific Gravity	1.17	g/cm ³
Chlorine Content - Saponifiable	0.0100	wt%
Color - G, Max	1.0	
Epoxy Equivalent	185 g/ep	
Thermoset	Nominal Value	Unit
Thermoset Mix Viscosity (25°C)	8000	cP

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT