# SARANEX™ 553

#### Coextruded Barrier Film

#### The Dow Chemical Company

#### Message:

 $\mathsf{SARANEX}^{\mathsf{m}}\ 553\ \mathsf{Clear}\ \mathsf{Coextruded}\ \mathsf{Barrier}\ \mathsf{Film}\ \mathsf{is}\ \mathsf{a}\ \mathsf{multi-layer}\ \mathsf{film}\ \mathsf{designed}\ \mathsf{for}\ \mathsf{use}\ \mathsf{in}\ \mathsf{packaging},\ \mathsf{converting}\ \mathsf{and}\ \mathsf{industrial}\ \mathsf{liner}\ \mathsf{applications}.$ 

General Characteristics:

Excellent barrier to oxygen, water vapor, flavors and aromas

Good clarity

Heat sealable

Complies with U.S. FDA requirements for food contact applications

Complies with EU, No 10/2011

Contact your Dow representative for more information on food contact compliance

Available Widths: 18 to 40 inches or 60 to 82 inches (460 to 1065 mm or 1525 to 2160 mm)

Available Core Sizes: 3 or 6 inch cores

Treatment: One side corona treatment available

General Information			
Agency Ratings	EU No 10/2011		
	FDA Food Contact, Unspecified Rating		
Forms	Film		
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (vs. Itself - Dynamic)	0.20		Internal Method
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	76	μm	
Film Thickness - Recommended / Available	3.0 mil (76.2 μ)		
Tensile Strength			ASTM D882
MD : Break, 76 μm	20.7	MPa	
TD : Break, 76 µm	20.7	MPa	
Tensile Elongation			ASTM D882
MD : Break, 76 μm	440	%	
TD : Break, 76 µm	510	%	
Oxygen Transmission Rate (23°C, 50% RH,			
76 μm)	4.3	cm³/m²/24 hr	ASTM D3985
Water Vapor Transmission Rate (38°C, 90%			
RH, 76 μm)	2.9	g/m²/24 hr	ASTM F1249
Heat Seal Strength			ASTM F88
177°C, 76.2 μm <sup>1</sup>	740	N/m	
MD, 30 psi, 1.0 sec : 177°C, 76.2 μm	860	N/m	
Yield (76.2 μm)	12.9	m²/kg	ASTM D4321
NOTE			
1.	TD, 30 psi, 1.0 sec		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2