

megol® DP2339 50

Styrene Ethylene Butylene Styrene Block Copolymer

API SpA

Message:

megol® DP2339 50 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) product. It can be processed by injection molding and is available in Europe.

Characteristics include:

- Chemical Resistant
- Eco-Friendly/Green
- Fast Molding Cycle
- Good Processability
- Good UV Resistance

General Information			
Features	Acid Resistant		
	Base Resistant		
	Detergent Resistant		
	Fast Molding Cycle		
	Good Chemical Resistance		
	Good Processability		
	Good UV Resistance		
	Good Weather Resistance		
	High Heat Resistance		
	Low Temperature Resistant		
	Ozone Resistant		
	Recyclable Material		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	50		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	3.20	MPa	
100% Strain	2.10	MPa	
300% Strain	2.50	MPa	
Tensile Elongation (Break)	500	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ¹	16.0	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 72 hr	25	%	

70°C, 24 hr	65	%
100°C, 24 hr	72	%

NOTE

1.
- Without Notch

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

