

Maxiglas® MG845

Polymethyl Methacrylate Acrylic

Maxiglas Corporation

Message:

Maxiglas® is a continuous mass polymerization acrylic pellet that has outstanding optical properties, excellent weather resistance, uniform color and impact resistance. It has exceptional freedom from warpage, cracks, scratches, blisters, voids, foreign matter, and other defects which may affect appearance or serviceability.

Applications:

- Extruded sheets for signage, displays and building material
- Automotive parts such as tail lamps, meter covers and sun visors
- General sundries such as tableware, kitchenware, giftware and bathroom accessories
- Optical lenses such as sunglasses, reading glasses and camera lenses
- Light guide panels for LCD displays

General Information	
Features	Good Weather Resistance
	Opticals
Uses	Automotive Applications
	Automotive Backlights
	Automotive Interior Parts
	Bathroom Accessories
	Building Materials
	Decorative Displays
	Displays
	Kitchenware
	LCD Applications
	Lighting Applications
	Optical Applications
	Toys
Forms	Pellets
Processing Method	Compression Molding
	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	4.5	g/10 min	ASTM D1238
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method

Tensile Strength	72.6	MPa	ASTM D638
Tensile Elongation (Break)	6.0	%	ASTM D638
Flexural Modulus	3330	MPa	ASTM D790
Flexural Strength	108	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	16	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	100	°C	ASTM D648
Vicat Softening Temperature	114	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542
Transmittance (3000 μm)	93.0	%	ASTM D1003
Haze (3000 μm)	0.30	%	ASTM D1003
Additional Information	Nominal Value	Unit	
Foreign Material ¹	< 0.0500	mm ²	
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0	hr	
Rear Temperature	190 to 240	°C	
Middle Temperature	190 to 240	°C	
Front Temperature	190 to 240	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Pressure	2.76 to 5.52	MPa	
Extrusion	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0	hr	
NOTE			
1.	Condition: 50g		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT