

REVOLVE® N-250

Polyethylene
Matrix Polymers

Message:

Revolve N-250 is a rotational moulding polyethylene general purpose grade. It has been designed to provide wide processing window, excellent mouldability without compromising impact strength. The grade is UV8 stabilised and it is the base of all standard colours and mottle effects.

General Information			
Additive	Long Term UV-8 Stabilizer		
Features	General Purpose		
	Good Impact Resistance		
	Good Moldability		
	Good Processability		
Uses	General Purpose		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
	Powder		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.935	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	7.0	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance			ASTM D1693
10% Igepal	50.0	hr	
100% Igepal	1000	hr	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	16.8	MPa	ISO 527-2/50
Flexural Modulus ¹	645	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
ARM Impact (-40°C, 3.00 mm)	102	J	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	47.0	°C	ISO 75-2/B
NOTE			
1.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

