

TABOREN PH 89 C 40

Polypropylene Homopolymer

SILON s.ro

Message:

TABOREN PH 89 C 40 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 40% calcium carbonate. It is available in Asia Pacific or Europe. Typical application: Automotive.

Characteristics include:

Heat Stabilizer

Homopolymer

General Information			
Filler / Reinforcement	Calcium Carbonate,40% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	Homopolymer		
Uses	Automotive Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	22.0	MPa	ISO 527-2/1B/50
Flexural Modulus	2700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	156	°C	ISO 306/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT