

Yuyao PA 01MG20

Polyamide 66/6 Copolymer

Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PA 01MG20 is a Polyamide 66/6 Copolymer (Nylon 66/6) product filled with 20% glass fiber. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PA 01MG20 include electrical/electronic applications, appliances, automotive and tools.

Characteristics include:

- Flame Rated
- Flame Retardant
- Good Processability
- Heat Resistant
- High Strength

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Electrical Properties		
	Good Processability		
	High Heat Resistance		
	High Strength		
Uses	Appliance Components		
	Automotive Under the Hood		
	Communication Applications		
	Computer Components		
	Connectors		
	Electrical Parts		
	Power/Other Tools		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	100	MPa	ASTM D638
Tensile Elongation (Break)	7.0	%	ASTM D638
Flexural Modulus	4500	MPa	ASTM D790
Flexural Strength	130	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	6.00	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	150	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 95.0	°C	
Drying Time	5.0 to 8.0	hr	
Processing (Melt) Temp	245 to 265	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	80.0 to 100	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

