

# Flexiblend® PP-1301

Polypropylene + EPDM Rubber

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

## Message:

Flexiblend® PP-1301 is a polypropylene with mineral filler and rubber modified compound. This grade has been developed for applications such as automotive bumper bar.

General Information			
Filler / Reinforcement	Mineral		
Features	Good Dimensional Stability		
	Low Temperature Toughness		
Uses	Automotive Applications		
	Automotive Bumper		
	Automotive Instrument Panel		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	17	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	23.0	MPa	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	2500	MPa	ASTM D790
Flexural Strength	30.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 4.00 mm)	110	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	60.0 to 80.0	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	180 to 190	°C	
Middle Temperature	190 to 200	°C	
Front Temperature	200 to 210	°C	

Nozzle Temperature	210 to 220	°C
Mold Temperature	60.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

