Zeoforte® ZSC 2298L

Acrylonitrile Butadiene Rubber

Zeon Chemicals L.P.

Message:

Nano-Composite Hydrogenated Nitrile Rubber - Zeon Super Composite

Main Characteristics & Applications

Zetpol composite, new grades with high dimensional stability and low heat-build-up, excellent tear resistance, abrasion resistance and good elongation at high hardness, excellent dynamic properties, used for timing belts, poly-V-belts and printing rollers.

General Information		
Features	Good Abrasion Resistance	
	Good Dimensional Stability Good Tear Strength	
	High Elongation	
	High Hardness	
Uses	Belts/Belt Repair	
	Rollers	
Physical	Nominal Value	Unit
Specific Gravity	1.32	g/cm³
Mooney Viscosity (ML 1+4, 100°C)	65 to 95	MU
Bound Acrylonitrile ¹	36.0	wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

mg/100 mg

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

28.0

Measured on base polymer.

Measured on base polymer.

Tel: +86 21 5895 8519

Iodine Value ²

NOTE 1.

2.

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

