

# ALTECH® PA66 C 1000/100

Polyamide 66  
ALBIS PLASTIC GmbH

Message:

ALTECH® PA66 C 1000/100 is a Polyamide 66 (Nylon 66) product. It is available in Asia Pacific, Europe, or North America. Typical application: Housings.  
Characteristics include:  
REACH Compliant  
RoHS Compliant  
Good Mold Release  
Heat Stabilizer  
High Flow

General Information			
Additive	Heat Stabilizer		
Features	Good Mold Release		
	Heat Stabilized		
	High Flow		
Uses	Housings		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Moisture - Karl Fischer	0.10	%	ISO 15512
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	100	kJ/m²	ISO 179/1eU
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80.0	°C	
Drying Time - Desiccant Dryer	2.0 to 12	hr	
Suggested Max Moisture	0.15	%	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	40.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT