

Precision Polymer N60W

Acrylonitrile Butadiene Rubber
Precision Polymer Engineering Ltd.

Message:

White Nitrile Butadiene Rubber (NBR), 55-65 °IRHD. Copolymer of acrylonitrile and butadiene. Formulated using only those ingredients determined by the United States Food and Drug Administration (FDA) to be in accordance with Code of Federal Regulations Title 21 (CFR21), Section 177.2600. Material formulated for repeated use in equipment associated with the production of foodstuffs intended for human consumption.

General Information			
Features	Copolymer		
	Compliance of Food Exposure		
Uses	Non-specific food applications		
Agency Ratings	FDA 21 CFR 177.2600		
Hardness	Nominal Value		Test Method
IRHD Hardness	57		ASTM D1415, ISO 48
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	13.0	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	350	%	ASTM D412, ISO 37
Compression Set			
100°C, 24 hr	45	%	ASTM D395B
100°C, 24 hr ¹	45	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (100°C, 70 hr)	-10	%	ASTM D412, ISO 37
Change in Ultimate Elongation in Air (100°C, 70 hr)	-25	%	ASTM D412, ISO 37
Change in IRHD Hardness in Air (100°C, 70 hr)	10		ASTM D573, ISO 188
Thermal	Nominal Value	Unit	
Maximum Operating Temperature	120	°C	
Low Temperature Resistance - Non-brittle after 3 mins	-40	°C	
Additional Information	Nominal Value	Unit	
Minimum Operating Temperature: -40°C (-40°F)			
NOTE			
1.	Type B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

