

Ebalta MG 321 FR-S / Comp. A+B

Polyurethane
Ebalta Kunststoff GmbH

Message:

ebalta MG 321 FR-S is processed on a two-component low pressure device.
After grinding with a sand paper , grit 280, the surface can be varnished with a commercial lacquer. For better adhesion we recommend the use of a primer coat. Nitrocellulose lacquers have a better adhesion on polyurethane surfaces than on acryl-lacquer-systems.

Applications
Cladding parts EDP field
Cladding parts medical sector
Interior / Exterior of rail vehicle

Properties
self-extinguishing according to UL 94 V0-FileE191776, Vol. 1
self-extinguishing according to UL 94 5 VA, File E191776, Vol. 1
Classification DIN 5510-2
precautionary fire protection in rail vehicles
for 4 mm wall thickness: S-3; SR1; ST2
high heat resistance
big wall thickness possible

General Information			
Features	High Heat Resistance		
	Self Extinguishing		
Appearance	Natural Color		
Processing Method	Casting		
Hardness	Nominal Value		Test Method
Shore Hardness (Shore D)	77 to 83		ISO 7619
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1900 to 2100	MPa	ISO 178
Flexural Stress	59.0 to 69.0	MPa	ISO 178
Compressive Stress	63.0 to 73.0	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	19 to 23	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	117 to 123	°C	ISO 75-2/B
Glass Transition Temperature	130 to 136	°C	DMA
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
	V-0		
3.00 mm	5VA		
4.00 mm	5VA		

Thermoset	Nominal Value	Unit
Thermoset Components		
	Mix Ratio by Volume: 51	
Hardener	Mix Ratio by Weight: 50	
	Mix Ratio by Weight: 100	
Resin	Mix Ratio by Volume: 100	
Post Cure Time		
80°C	4.0	hr
120°C	2.0	hr
Uncured Properties	Nominal Value	Unit
Density (20°C)	1.20 to 1.26	g/cm ³
Viscosity (25°C)	1.5 to 2.5	Pa·s
Curing Time (50°C)	0.25 to 0.33	hr
Pot Life (20°C)	0.83 to 1.0	min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

