

NILENE® E6 K20VA V2

Polypropylene Copolymer

Taro Plast S.p.A.

Message:

Polypropylene copolymer medium flow 20% glass fibres reinforced chemically coupled, flame retardant UL94 V2, good mechanical properties.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Additive	Flame retardancy		
Features	Copolymer		
	Chemical coupling		
	Medium liquidity		
	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction	0.55 - 0.75	%	Internal method
Flow direction	0.40 - 0.60	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	45.0	MPa	ISO 527-2/50
Tensile Strain (Break)	6.0	%	ISO 527-2/50
Flexural Modulus ¹	3500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	60	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	115	°C	ISO 75-2/A
Vicat Softening Temperature	105	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Glow Wire Flammability Index (1.00 mm)	850	°C	IEC 60695-2-12
Additional Information	Nominal Value	Unit	Test Method
Reinforcement Content ² (600°C)	20	%	ISO 3451
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 240	°C	
Mold Temperature	50.0 - 70.0	°C	
Injection Rate	Moderate		

Injection instructions

Pre-heat Temperature: 70 to 80°CPre-heat Time: 1 hr

NOTE

- | | |
|----|------------|
| 1. | 1.0 mm/min |
| 2. | 1 hr |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

