

Makrolon® 1095

Polycarbonate

Covestro - Polycarbonates

Message:

MVR (300 °C/1.2 kg) 6.0 cm³/10 min; 15 % glass fiber reinforced; UL 94V-0/3.0 mm; high viscosity; easy release; injection molding - melt temperature 310 - 330 °C; extrusion; available in opaque colors only; housings for power tools

General Information	
UL YellowCard	E41613-233175
Filler / Reinforcement	Glass Fiber,15% Filler by Weight
Features	Good Mold Release
	High Viscosity
Uses	Housings
	Power/Other Tools
RoHS Compliance	RoHS Compliant
Appearance	Colors Available
	Opaque
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.29	g/cm ³	ISO 1183
Apparent Density ¹	0.64	g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	6.00	cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 294-4
Across Flow : 2.00 mm	0.45	%	
Flow : 2.00 mm	0.45	%	
Water Absorption			ISO 62
Saturation, 23°C	0.24	%	
Equilibrium, 23°C, 50% RH	0.10	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	129	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4600	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/5
Yield, 23°C	64.0	MPa	

Break, 23°C	45.0	MPa	
Tensile Strain			ISO 527-2/5
Yield, 23°C	4.6	%	
Break, 23°C	12	%	
Flexural Modulus ³ (23°C)	4400	MPa	ISO 178
Flexural Stress ⁴			ISO 178
3.5% Strain,23°C	95.0	MPa	
23°C	105	MPa	
Flexural Strain at Flexural Strength (23°C) ⁵	5.8	%	ISO 178
Burning Rate - US-FMVSS (> 1.00 mm)	passed		ISO 3795
Flash Ignition Temperature	470	°C	ASTM D1929
Needle Flame Test			IEC 60695-11-5
Method F : 1.50 mm	2.0	min	
Method F : 2.00 mm	2.0	min	
Method F : 3.00 mm	2.0	min	
Method K : 1.50 mm	1.0	min	
Method K : 2.00 mm	1.0	min	
Method K : 3.00 mm	2.0	min	
Self Ignition Temperature	550	°C	ASTM D1929
Electrolytical Corrosion (23°C)	A1		IEC 60426
ISO Shortname	ISO 7391-PC,MR,(,,)-09-9,GF15		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁶ (23°C, Complete Break)	10	kJ/m ²	ISO 7391
Charpy Unnotched Impact Strength			ISO 179/1eU
-60°C, Complete Break	90	kJ/m ²	
-30°C, Complete Break	100	kJ/m ²	
23°C, Complete Break	120	kJ/m ²	
Notched Izod Impact Strength ⁷ (23°C, Complete Break)	10	kJ/m ²	ISO 7391
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-30°C	13.0	J	
23°C	25.0	J	
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-30°C	3000	N	
23°C	3600	N	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	141	°C	ISO 75-2/B
1.8 MPa, Unannealed	135	°C	ISO 75-2/A
Vicat Softening Temperature			
--	142	°C	ISO 306/B50

--	145	°C	ISO 306/B120
Ball Pressure Test (136°C)	Pass		IEC 60695-10-2
CLTE			ISO 11359-2
Flow : 23 to 55°C	3.5E-5	cm/cm/°C	
Transverse : 23 to 55°C	6.5E-5	cm/cm/°C	
RTI Elec (1.50 mm)	80.0	°C	UL 746
RTI Imp (1.50 mm)	80.0	°C	UL 746
RTI Str (1.50 mm)	80.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+16	ohms·cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	38	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.20		
23°C, 1 MHz	3.20		
Dissipation Factor			IEC 60250
23°C, 100 Hz	1.0E-3		
23°C, 1 MHz	9.0E-3		
Comparative Tracking Index			IEC 60112
Solution A	175	V	
Solution B	125	V	
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-2		
3.00 mm	V-0		
Glow Wire Flammability Index			IEC 60695-2-12
0.750 mm	850	°C	
1.50 mm	960	°C	
3.00 mm	960	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.750 mm	850	°C	
1.50 mm	900	°C	
3.00 mm	900	°C	
Oxygen Index ⁸	27	%	ISO 4589-2
NOTE			
1.	Pellets		
2.	60x60x2 mm, 500 bar		
3.	2.0 mm/min		
4.	2.0 mm/min		
5.	2 mm/min		
6.	Based on ISO 179-1eA, 3 mm		
7.	Based on ISO 180-A, 3 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

