

Staramide RX06027

Polyamide 66
Eurostar Engineering Plastics

Message:

Staramide RX06027 is a 30 % Glass Bead Reinforced Polyamide 66 Injection Molding Resin (also known as Staramide 66 30K S34/8)

General Information			
Filler / Reinforcement	Glass Bead,30% Filler by Weight		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3400	MPa	ISO 527-2/1
Tensile Stress (Yield)	50.0	MPa	ISO 527-2/5
Tensile Strain (Yield)	2.5	%	ISO 527-2/5
Flexural Modulus ¹	2900	MPa	ISO 178
Flexural Stress	83.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	5.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	25	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	61.0	°C	ISO 75-2/Af
CLTE			ISO 11359-2
Flow : 23 to 60°C	6.7E-5	cm/cm/°C	
Transverse : 23 to 60°C	6.7E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15	%	
Rear Temperature	265 to 275	°C	
Middle Temperature	270 to 280	°C	
Front Temperature	270 to 280	°C	
Processing (Melt) Temp	270 to 280	°C	
Mold Temperature	60.0 to 100	°C	
NOTE			
1.	2.0 mm/min		
2.	80*10*4		
3.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

