

LONGLITE® PBT 3030-200FR

Polybutylene Terephthalate

CCP Group

Message:

PBT 3030-200FR is a 30% glass fiber reinforced impact modified hydrolysis resistant natural color injection molding grade.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Impact Modifier		
Features	Hydrolysis Resistant		
	Impact Modified		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.49	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	20	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.80 to 1.1	%	
Flow	0.10 to 0.40	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9600	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	140	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.5	%	ISO 527-2
Flexural Modulus (23°C)	7700	MPa	ISO 178
Flexural Stress (23°C)	200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	210	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Melting Temperature	225	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength (2.00 mm)	23	kV/mm	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

Injection	Nominal Value	Unit
Drying Temperature	120 to 140	°C
Drying Time	4.0	hr
Processing (Melt) Temp	240 to 270	°C
Mold Temperature	60.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

