

NOTIO™ PN-2070

Thermoplastic Elastomer

Mitsui Chemicals America, Inc.

Message:

NOTIO™ is a flexible, low density, transparent elastomer with excellent heat resistance. The resin is not cross- linked and demonstrates superior elasticity. NOTIO's crystalline and amorphous structure (morphology) is controlled at the nano scale, allowing for the realization of properties that cannot be achieved with conventional elastomers.

General Information			
Features	Amorphous		
	Crystalline		
	Good Flexibility		
	High Elasticity		
	High Heat Resistance		
	Low Density		
Uses	Adhesives		
	Automotive Applications		
	Film		
	Packaging		
	Plastics Modification		
Appearance	Clear/Transparent		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.867	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	16.0	MPa	Internal Method
Tensile Strength ² (Break)	14.0	MPa	Internal Method
Tensile Elongation ³ (Break)	> 800	%	Internal Method
Elastomers	Nominal Value	Unit	Test Method
Tensile Set ⁴ (150% Strain)	12	%	Internal Method
Compression Set ⁵			Internal Method
23°C, 24 hr	20	%	
70°C, 24 hr	60	%	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-28.0	°C	ASTM D746

Glass Transition Temperature	125	°C	Internal Method
Optical	Nominal Value	Unit	Test Method
Haze (2000 μm, Compression Molded)	7.0	%	ASTM D1003
NOTE			
1.	JIS K7113-2		
2.	JIS K7113-2		
3.	JIS K7113-2		
4.	JIS K7113-2, 0.3 mm		
5.	JIS K7113-2, 12 mm, 25% compression		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

