

Xuchuan 6170/B-8280 (Sole)

Polyurethane

Xuchuan Chemical (Suzhou) Co., Ltd

Message:

Xuchuan 6170/B-8280 (Sole) is a Polyurethane product. It is available in Asia Pacific. Typical application: Consumer Goods.

Characteristics include:

High Strength

Wear Resistant

General Information		
Features	Good Abrasion Resistance	
	High Strength	
Uses	Footwear	
Physical	Nominal Value	Unit
Density	0.900 to 1.10	g/cm ³
Density		
A-6170 : 40°C	1.010 to 1.020	g/cm ³
B-8280 : 40°C	1.080 to 1.200	g/cm ³
Viscosity		
A-6170 : 40°C	1.00 to 1.40	Pa·s
B-8280 : 40°C	0.800 to 1.20	Pa·s
Ross Flex (23°C) ¹	No Crack	
Williams Abrasion	60.0 to 100	cc/php
Cream Time	6.0 to 8.0	sec
End of Rise Time	40.0 to 50.0	sec
Adhesion Strength - Between sole and mid-sole	39.2 to 58.8	kN/m
Free Rise Foam Density	470 to 500	kg/m ³
Preheat Temperature		
Part A	50 to 60	°C
Part B	50 to 60	°C
Preheat Time		
Part A	8.0 to 10.0	hr
Part B	8.0 to 12.0	hr
Processing Temperature		
Part A	40 to 45	°C
Part B	40 to 45	°C
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	62 to 72	
Elastomers	Nominal Value	Unit

Tensile Strength (Break)	8.00 to 11.0	MPa
Tensile Elongation (Break)	550 to 750	%
Tear Strength	25.0 to 40.0	kN/m
Thermoset	Nominal Value	Unit
Thermoset Components		
Part A	Mix Ratio by Weight: 100	
Part B	Mix Ratio by Weight: 69 to 71	
Demold Time	3.0 to 5.0	min
Injection	Nominal Value	Unit
Mold Temperature	45.0 to 55.0	°C
NOTE		
1.	100000 cycles, Break length 4 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

