

Elastron® D D400.D62.B

Styrene Butadiene Styrene Block Copolymer

Elastron USA, Inc.

Message:

A hard, black unfilled SBS based thermoplastic elastomer (TPE) compound designed for injection molding applications.
Bondable to: PP, EVA, PE

General Information			
Features	Block Copolymer		
	Bondability		
	High Hardness		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.910	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	2.3	%	
Across Flow	2.2	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	62		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	14.0	MPa	
300% Strain	17.9	MPa	
Tensile Strength (Break)	20.0	MPa	ASTM D412
Tensile Elongation (Break)	650	%	ASTM D412
Tear Strength	85.0	kN/m	ASTM D624
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Suggested Max Regrind	20	%	
Rear Temperature	150 to 170	°C	
Middle Temperature	160 to 180	°C	
Front Temperature	170 to 190	°C	
Nozzle Temperature	180 to 210	°C	
Mold Temperature	25.0 to 50.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

