

MAXAMID™ PA66-MOS2 BK

Polyamide 66

Pier One Polymers, Inc.

Message:

MAXAMID™PA66-MOS2 is a Nylon 66 with 2% MoS2 incorporated to provide excellent lubricity which significantly reduces the friction and improves the wear properties of injection molded parts.

General Information			
Additive	Molybdenum Disulfide Lubricant (2%)		
Features	Good Wear Resistance		
	Low Friction		
	Lubricated		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	93.1	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	20	%	ASTM D638
Flexural Modulus (23°C)	3790	MPa	ASTM D790
Flexural Strength (23°C)	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	37	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	83.8	°C	ASTM D648
Peak Melting Temperature	254	°C	ASTM D3418
Injection	Nominal Value	Unit	
Suggested Max Moisture	< 0.20	%	
Processing (Melt) Temp	290 to 305	°C	
Mold Temperature	38.0 to 93.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

