

Hifax ETA3041 YGYA BLK

Thermoplastic Polyolefin Elastomer

LyondellBasell Industries

Message:

Hifax ETA3041 YGYA BLK medium melt flow, 170 MPa flexural modulus, thermoplastic elastomeric olefin (TEO) resin has a good balance of flexibility and durability. It is typically used for a wide variety of molded-in color automotive exterior components.

For regulatory compliance information, see Hifax ETA3041 YGYA BLK Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

General Information			
Features	Good flexibility		
	Medium liquidity		
	Durability		
Uses	Application in Automobile Field		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	7.00	MPa	ISO 527-2
Flexural Modulus	170	MPa	ISO 178

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT