

# Hifax CB 1173 G/M 2700

Polyolefin

LyondellBasell Industries

## Message:

This is a provisional internal only product data sheet to allow creation of MSDS and RAPIDS. When material is commercialized a full product data sheet will be completed by responsible BU.

General Information			
Features	High Flow		
	High Impact Resistance		
Uses	Automotive Applications		
	Automotive Bumper		
	Automotive Exterior Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus <sup>1</sup> (23°C)	1400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	6.0	kJ/m <sup>2</sup>	
23°C	No Break		
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT