

RTP 900 M-825 Z

Polysulfone
RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

| General Information | | | |
|---|--------------------------------------|-------------------|-------------|
| Filler / Reinforcement | Mineral filler, 25% filler by weight | | |
| Agency Ratings | FDA not rated | | |
| RoHS Compliance | Contact manufacturer | | |
| Appearance | Black | | |
| | Natural color | | |
| Forms | Particle | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.45 | g/cm ³ | ASTM D792 |
| Molding Shrinkage - Flow (3.18 mm, Injection Molded) | 0.60 | % | ASTM D955 |
| Water Absorption (23°C, 24 hr) | 0.70 | % | ASTM D570 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus (Injection Molded) | 3790 | MPa | ASTM D638 |
| Tensile Strength | 69.0 | MPa | ASTM D638 |
| Flexural Modulus (Injection Molded) | 4130 | MPa | ASTM D790 |
| Flexural Strength (Injection Molded) | 121 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (3.18 mm, Injection Molded) | 53 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed, Injection Molded) | 174 | °C | ASTM D648 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating (1.50 mm) | V-2 | | UL 94 |
| Additional Information | | | |
| The value listed as Flammibility, UL 94, was tested in accordance with RTP Company methods. | | | |
| Injection | Nominal Value | Unit | |
| Rear Temperature | 321 - 360 | °C | |
| Middle Temperature | 321 - 360 | °C | |
| Front Temperature | 321 - 360 | °C | |
| Mold Temperature | 93.0 - 149 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

