

Braskem PE SLL218

Linear Low Density Polyethylene

Braskem

Message:

Description:

SLL218 is a Linear Low Density Polyethylene, copolymer of butene-1. Developed for cast film extrusion. Films obtained with this product show a good processing performance balanced with good optical and mechanical properties as well as processability. Very low gel amount. It contains antioxidant additives.

The minimum biobased content of this grade is 87%, determined according to ASTM D6866.

Applications:

Stretch films; liners; LDPE and HDPE blends and packages for general use.

Process:

Recommended processing conditions for film extrusion about 170 - 210 °C. The optimum processing conditions will vary according to the type of equipment used and cannot be considered as performance guarantee.

General Information			
Additive	Antioxidation		
Features	Low speed solidification crystal point		
	Optical		
	Antioxidation		
	Updatable resources		
	Compliance of Food Exposure		
Uses	Films		
	Mixing		
	General		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.3	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD: Fracture, 38 µm	40.0	MPa	ASTM D882
TD: Fracture, 38 µm	30.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture, 38 µm	1300	%	ASTM D882
TD: Fracture, 38 µm	1600	%	ASTM D882
Flexural Modulus			ASTM D790
1% Secant, MD : 38 µm	200	MPa	ASTM D790
1% Secant, TD : 38 µm	230	MPa	ASTM D790

Dart Drop Impact ¹	100	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 38 μm	150	g	ASTM D1922
TD : 38 μm	190	g	ASTM D1922
Additional Information	Nominal Value	Unit	Test Method
Biobased Content	> 87	%	ASTM D6866
NOTE			

1. F50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

