

LNP™ LUBRICOMP™ DBL32 compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP LUBRICOMP DBL32 is a compound based on Polycarbonate resin containing PTFE, Carbon Fiber. Added features of this material include: Electrically Conductive, Internally Lubricated.
Also known as: LNP* LUBRICOMP* Compound DBL-4032
Product reorder name: DBL32

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Additive	PTFE lubricant		
Features	Conductivity		
	Lubrication		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.70 - 0.90	%	ASTM D955
Transverse flow: 24 hours	0.90 - 1.1	%	ASTM D955
Vertical flow direction: 24 hours	0.96	%	ISO 294-4
Flow direction: 24 hours	0.80	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2070	MPa	ASTM D638
--	2580	MPa	ISO 527-2/1
Tensile Strength			
Yield	42.7	MPa	ASTM D638
Yield	43.0	MPa	ISO 527-2
Fracture	38.6	MPa	ASTM D638
Fracture	38.0	MPa	ISO 527-2
Tensile Elongation			
Yield	5.4	%	ASTM D638
Yield	5.1	%	ISO 527-2
Fracture	22	%	ASTM D638
Fracture	18	%	ISO 527-2
Flexural Modulus			
--	2760	MPa	ASTM D790
--	2400	MPa	ISO 178
Flexural Stress	69.0	MPa	ISO 178

Coefficient of Friction		ASTM D3702 Modified	
With self-dynamics	0.42	ASTM D3702 Modified	
With Self-Static	0.48	ASTM D3702 Modified	
Wear Factor - Washer	139	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	190	J/m	ASTM D256
23°C ²	14	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1500	J/m	ASTM D4812
23°C ³	110	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	31.5	J	ASTM D3763
--	25.8	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	143	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ⁴	139	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	135	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁵	135	°C	ISO 75-2/Af
Linear thermal expansion coefficient			
Flow: -40 to 40°C	5.4E-5	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	5.3E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	5.9E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	6.0E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 - 304	°C	
Middle Temperature	310 - 321	°C	
Front Temperature	321 - 332	°C	
Processing (Melt) Temp	304 - 327	°C	
Mold Temperature	82.2 - 110	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

